FRODUCT BULLETIN GYPSUM PRODUCTS	GYPSUM DUNNAGE 1/4" THICK	BULLETIN NO: DATE: PAGE:	B-50 12/31/67 1 of 1
		CANCELS: DATE:	B-50 10/12/65

CORE FORMULA (Lbs/MSF)						
	Long Beach	Antioch	Seattle	Rosario	<u>Jacksonville</u>	Delanco
Board Stucco (S-1, S-2)	575-725	575-725	575 <b>-</b> 725	575-725	575-725	575-725
Paper Fiber (BG-1)	7.0	7.0	7.0	7.0	7.0	7.0
Starch (RM-B11A)	4.5-5.5	4.5-5.5	4.5-5.5	4.5-5.5	4.5-5.5	4.5-5.5
Core Foaming Agent: Resin (BG-1) ALS (BG-1) AAS (BG-1)	0.2-0.6	0.2-0.6	0.7-1.3	0.2-0.6	0.2-0.6	0.2-0.6
Lignin (8G-1)	1.5	1.5	3.0	1.5	1.5	3.0
					<b>-</b> .	v
End Trim (BG-1)	20-30	20-30	20-30		20-30	20-30
Potassium Sulfate (BG-1)	0-2.0	0-2.0	0-2.0	0-2.0	0-2.0	0-2.0
Retarder (BG-1)				0-0,2		

Paper Liners: Face - Greyback or Coreboard Paper
Back - Greyback Paper

FRODUCT SPECIFICATIONS:	All Plants
Wet Weight	1400-1500
Dry Weight	900-1050